

Eucocrete Activator

Surface Hardener and Corrosion Inhibitor - Aqueous Solution

PRODUCT DESCRIPTION

Eucocrete Activator is a chemically blended aqueous solution, free of chlorides, especially formulated as a Penetrative Corrosion Inhibitor that significantly hardens the surface and increases the durability of concrete and enhances bond of toppings.

USAGE/PURPOSE

As a performance and durability enhancer of existing concrete surfaces:

- Repairs hair line cracks in concrete
- Densifies and hardens the surface layer
- Stops surface dusting
- Increases impermeability, chemical resistance and durability
- Restores the protective properties of the concrete against reinforcement corrosion

On new hardening concrete:

- Reduces water loss by approximately 20%
- Promotes efficient cement hydration
- Stops surface dusting
- Reduces surface cracking
- Increases surface hardness, impermeability and durability
- Enhances concrete protective properties against steel reinforcement corrosion

As a primer for most cementitious renders and polymeric coatings:

- Increases the adhesive bond strength of the renders and polymeric coatings

As a treatment of brickwork joints:

- Works as a hardener and durability enhancer of brickwork joints

PACKAGING

- 20 Litre Pail
- 1000 Litre Pail

AREAS OF USE

- Restoration of degraded concrete surfaces
- Approved to use on Heritage sites
- Dust proofing of factory floors
- Surface hardening and abrasion resistance of concrete surfaces - floors, road works, bridge decks etc
- Reinstatement of poorly finished concrete
- Primer for cementitious renders
- Water retention agent for new hardening concrete



LIMITATIONS

Not suitable for use as a curing compound (not tested to AS3799)

SHELF LIFE

12 months when stored as recommended in original unopened packaging.

STORAGE

Store in original, undamaged packaging in a clean, dry, protected location. Stir well before use.

SUBSTRATE PREPARATION

- Eucocrete Activator must be applied to a clean surface free of contaminants.
- Pressure washing is recommended as minimum preparation.
- Prepared surface should be surface, saturated dry.

APPLICATION

- Eucocrete Activator is normally applied as a single coat, coverage rate approximately 3-5m² per litre.
- Double coating is deemed necessary for badly degraded concrete, the second coat can be applied after 2-4 hours, when the first coat is fully impregnated into the concrete.

CURING TIME

Treated concrete can be put into service as soon as the surface is dry.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	STANDARD	TYPICAL VALUES
Friction Abrasion Resistance		Mass loss is reduced by up to 40 times
Impact Abrasion Resistance	AS/NZS 4456.9-2003	Abrasion resistance is increased
Chloride Ion Diffusion	NT Build 443 1995-11	Reduced approx two times
Reinforcement Corrosion Inhibition	Polarisation Curves Method	Steel reinforcement is passivated and hence corrosion is inhibited
Water Absorption	Taywood Engineering Test	Absorption is decreased by approx 25%
Retention for new hardening concrete	AS 3799-1998	Water loss is reduced by approx 20%
Slip Resistance	AS/NZS 4586-2004	Unchanged by treatment

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco CPG Australia Pty Ltd has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

Tremco CPG Australia Pty Ltd products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG Australia written instructions and (b) in any application recommended by Tremco CPG Australia, but which is proved to be defective, will be replaced free of charge.

Any information provided by Tremco CPG Australia in this document in relation to Tremco CPG Australia's goods or their use is given in good faith and is believed by Tremco CPG Australia to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. Tremco CPG Australia makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.

CONTACT OUR TEAM

Tremco CPG Australia Pty Ltd

ABN: 25 000 024 064

Unit 12, 4 Southridge Street

Eastern Creek, NSW 2766

P: (02) 9638 2755

F: (02) 9638 2955

E: tremco@tremco.com.au